

WHAT IS CLAIMED IS:

1. A high throughput method for screening lubricating oil composition samples for compatibility with elastomers, under program control, comprising the steps of:

(a) providing a plurality of different lubricating oil composition samples, each  
5 sample comprising (i) a major amount of at least one base oil of lubricating viscosity and  
(ii) a minor amount of at least one lubricating oil additive;

(b) providing at least one elastomer;

(c) measuring the elastomer compatibility of each sample to provide elastomer compatibility data for each sample; and,

10 (d) outputting the results of step (c).

2. The method of claim 1, wherein the at least one base oil of lubricating viscosity is a natural or synthetic oil.

15 3. The method of claim 1, wherein the at least one lubricating oil additive is selected from the group consisting of antioxidants, anti-wear agents, detergents, rust inhibitors, dehazing agents, demulsifying agents, metal deactivating agents, friction modifiers, pour point depressants, antifoaming agents, co-solvents, package compatibilisers, corrosion-inhibitors, ashless dispersants, dyes, extreme pressure agents  
20 and mixtures thereof.

4. The method of claim 1, wherein the at least one elastomer is selected from the group consisting of olefinic elastomers, styrenic elastomers, poly(ether/ester) elastomers, polyacrylate elastomers, natural rubbers, synthetic rubbers, elastomer seals and mixtures thereof.

5

5. The method of claim 1, wherein the at least one elastomer is an elastomer seal.

6. The method of claim 1, wherein the step of measuring the elastomer compatibility of each sample comprises immersing the at least one elastomer in the sample at a predetermined temperature for a predetermined period of time and measuring the tensile strength and/or elongation of the elastomer to determine the elastomer compatibility of the sample.

10

15

7. The method of claim 6, wherein the predetermined temperature is about 100°C to about 400°C and the predetermined time is about 100 hours to about 400 hours.

8. The method of claim 1, wherein the elastomer compatibility measurement of step (c) comprises a tensile strength measurement or an elongation measurement.

20

9. The method of claim 8, wherein the tensile strength measurement is compared with a predetermined tensile strength measurement of the elastomer.

10. The method of claim 8, wherein the elongation measurement is compared with a predetermined elongation measurement of the elastomer.

11. The method of claim 1, wherein the lubricating oil composition test samples  
5 have a volume of no more than about 50 ml.

12. The method of claim 1, wherein the lubricating oil composition test samples have a volume of no more than about 20 ml.

10 13. The method of claim 1, wherein the lubricating oil composition test samples have a volume of no more than about 15 ml.

14. The method of claim 1, wherein the lubricating oil composition test samples have a volume of no more than about 10 ml.

15

15. The method of claim 6, further comprising thermally conditioning the elastomer prior to immersing the elastomer in the sample.

16. The method of claim 15, wherein the elastomer is thermally conditioned at a  
20 temperature of about 100°C to about 200°C for about 20 hours to about 60 hours.

17. The method of claim 1, wherein a robotic assembly selectively retrieves the individual test receptacles from an array of test receptacles and selectively retrieves the at least one elastomer and individually positions the test receptacles and the at least one elastomer in a testing station for determination of the elastomer compatability.

5

18. The method of claim 17, wherein the robotic assembly is controlled by a computer.

19. The method of claim 1, wherein the step of outputting comprises storing the result of step (c) on a data carrier.

10

20. The method of claim 1, further comprising the step of using the result of step (d) as a basis for obtaining a result of further calculations.

15

21. The method of claim 1, wherein the at least one lubricating oil additive of the lubricating oil composition further comprises a diluent oil to form an additive concentrate.

20

22. A system for determining compatibility of lubricating oil composition samples with elastomers, under program control, comprising:

a) a plurality of test receptacles, each receptacle containing a different lubricating oil composition sample comprising (i) a major amount of at least one base oil of lubricating viscosity and (ii) a minor amount of at least one lubricating oil additive;

b) receptacle moving means for individually positioning the test receptacles in a testing station for measurement of elastomer compatibility of the respective sample with at least one elastomer;

c) elastomer moving means for individually positioning at least one elastomer in the testing station for measurement of elastomer compatibility with the respective sample;

d) means for measuring the elastomer compatibility of the sample with the elastomer in the testing station to obtain elastomer compatibility data associated with the sample and for transferring the elastomer compatibility data to a computer controller.

10

23. The system of claim 22, wherein the receptacle moving means comprises a movable carriage.

24. The system of claim 22, wherein the receptacle moving means comprises a robotic assembly having a movable arm for grasping and moving a selected individual receptacle.

15

25. The system of claim 22, wherein the elastomer moving means comprises a movable carriage.

20

26. The system of claim 22, wherein the elastomer moving means comprises a robotic assembly having a movable arm for grasping and moving an elastomer.

27. The system of claim 22, wherein each test receptacle has a bar code affixed to an outer surface thereof.

28. The system of claim 27, further comprising a bar code reader.

5

29. The system of claim 22, wherein the base oil of lubricating viscosity is a natural or synthetic oil.

30. The system of claim 22, wherein the at least one lubricating oil additive is  
10 selected from the group consisting of antioxidants, anti-wear agents, detergents, rust inhibitors, dehazing agents, demulsifying agents, metal deactivating agents, friction modifiers, pour point depressants, antifoaming agents, co-solvents, package compatibilisers, corrosion-inhibitors, ashless dispersants, dyes, extreme pressure agents and mixtures thereof.

15

31. The system of claim 22, wherein the means for measuring the elastomer compatibility comprises a means for measuring tensile strength.

32. The system of claim 22, wherein the means for measuring the elastomer  
20 compatibility comprises a means for measuring elongation.

33. A combinatorial lubricating oil composition library comprising lubricating oil composition elastomer compatability data for a plurality of different lubricating oil compositions comprising (a) a major amount of a base oil of lubricating viscosity and (b) at least one lubricating oil additive.

5

34. The combinatorial library of claim 33, wherein the lubricating oil composition elastomer compatability data is selected from the group consisting of tensile strength measurements, elongation measurements, and combinations thereof.